

APPENDIX C.3
PAINT AND OIL SAMPLE ANALYTICAL RESULTS

Dewline C5 PAINT/OIL							
Parameter	MDL (mg/kg)	A C5P-001	A C5P-002	A C5P-003	A C5P-004	A C5P-005	A C5PCB-1
METALS							
Arsenic	0.1	170	1	0.5	0.7	38	-
Selenium	0.5	6.3	<	<	<	2.2	-
Mercury	0.05	49	<	0.22	2.9	14	-
Barium	1	120	13000	9900	55	48	-
Beryllium	1	<	<	<	<	<	-
Cadmium	1	15	38	40	<	11	-
Chromium	1	210	7	5	22	64	-
Lead	10	330	210	40	52	1100	-
Nickel	5	42	<	<	<	15	-
Silver	5	<	<	<	<	<	-
PCB (Oil)	0.01 mg/L	-	-	-	-	-	<

< = below detection limit

- = not analyzed

Metals	Test Method
Barium, Beryllium, Cadmium	Method 6010
Chromium, Lead, Nickel, Silver	Method 6010
Arsenic, Selenium	Method 7061,7741
Mercury	Method 7471